

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
10 November 2005 (10.11.2005)

PCT

(10) International Publication Number
WO 2005/105915 A1

- (51) International Patent Classification⁷: **C08L 23/16**, C08K 5/09
- (21) International Application Number:
PCT/IT2005/000236
- (22) International Filing Date: 21 April 2005 (21.04.2005)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
VR2004A000074 3 May 2004 (03.05.2004) IT
- (71) Applicant (*for all designated States except US*):
SO.FTER. S.P.A. [IT/IT]; Via Mastro Giorgio, 2,
I-47100 Forlì (IT).
- (72) Inventor; and
- (75) Inventor/Applicant (*for US only*): CARFAGNINI, Italo
[IT/IT]; Via Mastro Giorgio, 2, I-47100 Forlì (IT).
- (74) Agent: SANDRI, Sandro; Europatent - Euromark S.r.l.,
Via Locatelli, 20, I-37122 Verona (IT).
- (84) Designated States (*unless otherwise indicated, for every kind of regional protection available*): ARIPO (BW, GH, GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU, IE, IS, IT, LT, LU, MC, NL, PL, PT, RO, SE, SI, SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, ML, MR, NE, SN, TD, TG).
- Published:**
— *with international search report*
- For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.*

(54) Title: PLASTO-ELASTOMERIC COMPOSITIONS

(57) Abstract: An EPDM terpolymer and polyolefin based plasto-elastomeric composition containing the elastomeric phase partially or fully cross-linked, where for cross-linking it is possible to use, alternatively, an alkylphenol - formaldehyde non-halogenated resin or a phenol - formaldehyde non-halogenated resole resin, and where an aromatic carboxylic acid is used for cross-linking, in particular salicylic acid, fillers of mineral origin being added, either directly during the compounding step with cross-linking, or subsequently to the material that is already cross-linked, to achieve a total specific gravity of up to 2 kg/dm³ with hardnesses ranging from ShA 40 to ShD 50. The fillers of mineral origin being in a quantity which may reach almost 90% by weight of the composition.

WO 2005/105915 A1